Terbrack Kunststoff GmbH & Co.KG

Tekalen® T 3000 R short mark. PE - UHMW (reg.)

properties: good sliding properties, good wear properties, chemical resistance,

no water absorption

For regenerated slight deviations of the technical values are possible!

colour: Black/green, confetti

technical data sheet – product information

physical properties			
properties	test methods	units	results
molecular weight (average molecular weight)	-	g/mol	~ 3 - 6*10 ⁶
density	ISO 1183	g/cm³	≥ 0,93
water absorption	ISO 62	%	< 0,01
flame classification	UL94	-	НВ

mechanical properties			
yield stress	IS <mark>O 5</mark> 27	N/mm²	≥ 17
elongation at yield	IS <mark>O 5</mark> 27	%	≥8
modulus of elasticity	IS <mark>O 5</mark> 27	MPa	≥ 700
impact strength (Charpy)	IS <mark>O 1</mark> 79	kJ/m²	Without breakage
notched impact strength (Charpy)	ISO 11542-2	kJ/m²	≥ 80
ball indentation hardness	IS <mark>O 2</mark> 039-1	N/mm²	~ 40
shore D hardness of 15-s value	ISO 868	-	~ 63
dynamic coefficient of friction	-	-	~ 0,2
wear (Sand-Slurry)	ISO 15527	%	~ 130

thermal properties				
melting range DSC, 10K/min.	ISO	<mark>O 3</mark> 146	°C	~ 130 - 135
coefficient of thermal expansion	n ISO	<mark>O 1</mark> 1359	K^{-1}	ca. $2*10^{-4}$
between 23 °C and 60 °C				
thermal conductivity	ISO	<mark>O 5</mark> 2612	W	~ 0,41
			$\overline{m*K}$	
usage temperature (max.)	-		°C	80
usage temperature short term	٠,		°C	100
usage temperature (min.)	/-		°C	- 200

electrical properties				
surface resistivity	IFC 60093	Ohm	> 10 ¹²	

Conformances according to:

EU-plastics directive 10/2011/EG

TERBRACK

August 2020

Notes for the user: The values given in this data sheet are based on a sheet with a 40mm thickness. Depending on the thickness the technical values may vary during processing.

The technical data given in this sheet correspond to our current state of knowledge and should not be construed as an agreement or guarantee regarding certain properties of our products. The decision on the suitability of a particular material for a specific application is up to the user. We reserve the right to modify the given data. Errors of the given data are reserved. The document was produced by machine and is valid without signature.

Terbrack Kunststoff GmbH & Co.KG P.O. Box 1353 D-48686 Vreden phone: +49 (0) 2564 / 393 - 0 www.terbrack.de Plastic factory
Von-Siemens-Straße 12 – 14
D-48691 Vreden-Gaxel
E-Mail: info@terbrack.de